

Product Parameters

Product Name: Hyper ABS

Extruder Temperature: 230-270°C

Hotbed Temperature: 75-95°C

Printing Speed: <350mm/s

Impact Resistance: 19 kJ/m²

Tensile Strength: 30.4 ± 0.6 Mpa

Bending Strength: 48.1 ± 0.2 Mpa

Filament Diameter: 1.75±0.05mm

N.W: 1Kg/2.2lb

G.W: 1.29Kg/2.8lb

Packing Size: 450x440x230mm